Refining of compounds by zone melting

- IN Eckschlager, Karel; Veprek-Siska, Josef
- PA Czech.
- SO Czech., 3 pp.
- PI CS 158897 19750715
- AI CS 70-6192 19700909
- DT Patent
- LA Unavailable
- AB An app. for simultaneous zone melting and melt electrolysis consists of a wheeled mobile tank for the refined material with an elec. conductive bottom as a cathode, a 2nd electrode or several electrodes, and one or several heating elements (e.g. a funnel furnace) and cooling elements placed along the tank track. Refining in the app. with 1 electrode and heater is demonstrated on NaOH.H2O (I) (1200 g, m.p. 68.degree.) contg. 6 .times. 10-3% Fe which by 10 zone passages and electrolyses with a rotating anode (c.d. 7 mA/cm2) followed by 8 zone passages without electrolysis gave 525 g I contg. 10-6% Fe. The same procedure without electrolysis gave 230 g I contg. 5 .times. 10-6% Fe. The zone width and transport velocity were 5 cm and 0.6 cm/hr, resp., in both cases.